


CMET® T703 is an oil soluble ashless antirust additive made by neutralization of alkenyl Imidazoline and dodecenyl succinic acid. This product has excellent acid neutralization ability. Its polar groups can be firmly adsorbed on the metal surface, forming a tight single molecule or multi molecule protective layer on the metal surface and maintaining sufficient oil film thickness to prevent corrosive media from contacting metal. It has good antirust ability for both ferrous and non-ferrous metals.

CHEMICAL COMPOSITION



Heptadecenyl imidazoline succinate

TYPICAL PROPERTIES

Test Item	Typical Data	Method
Appearance	Reddish brown liquid or semi solid	Visual inspection
Viscosity at 100°C, mm ² /s	48.0	GB/T 265
Alkaline nitrogen content, %	1.6	SH/T 0413
Acid number, mgKOH/g	38.0	GB/T 7304
Oil solubility	Intersolubility	Visual inspection

Note: The above analytical data are not specifications.

PERFORMANCE CHARACTERISTICS

- Good oil solubility, good resistance to wet heat for ferrous, and certain protection for nonferrous metals (copper, aluminum and alloy)
- Good acid neutralization ability and can play a solubilizing role in other types of auxiliary rust inhibitors

APPLICATION

- Suitable for modulating lubricating oils and greases with excellent rust resistance

USAGE METHOD

- Added to the formulation directly and compatibility needs to be tested before adding
- Recommended treat level: 0.5-2.0%

RELATIVE PRODUCTS

- T703

PACKAGING AND STORAGE

Packaging	50kg plastic drum or 180kg steel drum (Net weight)
Storage conditions	Store in a cool, dry, well-ventilated warehouse

HANDLING INFORMATION

Avoid contact with skin, eyes and clothing. Operate in accordance with good industrial health and safety practices. Please refer to material safety data sheet (MSDS) for additional handling information on **CMET® T703**.

Luoyang Pacific United Petrochemical Co., Ltd. (UNPChemicals) hopes that the information provided will be helpful to you. The information provided in this document has been prepared by technicians and is true and accurate as of the date of this document. However, please note that the conditions of your use and application of our products, technical assistance and information (whether orally, in writing or through product evaluation), including any suggested formulations and recommendations, are outside our control. UNPChemicals makes no representations, warranties or warranties (whether express, implied, statutory or otherwise), or implied warranties as to the completeness, accuracy or timeliness of any information. It is therefore important that you test our products, technical assistance and information, including how they are packaged, to determine their performance, efficacy and safety. You are solely responsible for the performance, efficacy and safety of any products you produce. UNPChemicals assumes no liability and you bear all risks and liabilities for any use or handling of any material. Nothing in this document should be interpreted as suggesting the use of any product that conflicts with the patent covering any material or its use. No license is implied or granted under the claims of any patent. We will provide consistent quality products within our sales conditions.